

PaintersChoice

PC-47

RAPID CURE CLEARCOAT

PC-47 Rapid Cure Clearcoat is a rapid cure clearcoat, designed to increase production and cycle time, in the shop. This fast drying clearcoat can be used on spot and panel repairs, as well as overall applications. PC-47 offers excellent flow and self leveling properties. Its superior gloss, and increased buff times are sure to increase productivity. This 4:1 clearcoat must be activated with PC4XAF PC4XAN, or PC4XAS Activator.



Apply basecoat per manufacturers recommended instructions. Mix 3 parts **PC-47 Rapid Cure Clearcoat** with 1 part **PC4XA activator** to 1 part **PC-870 Urethane Reducer**.



For small jobs, such as doors and fenders, one tack coat of clear can be applied, followed by one full wet coat of clear with no flash time between coats. Tack coat must be applied evenly to achieve proper mil. thickness.



For maximum gloss appearance, apply one wet coat of clear. Allow a flash time of 10-15 minutes, followed with a second wet coat of clear.



Dust free in 5-15 minutes depending on weather conditions and activator used.
Tack free in 5-15 minutes depending on weather conditions and activator used.
Force dry after a 10 minute flash. Bake for 30 minutes at 140 °F



Sand PC-47 Rapid Cure Clearcoat after 1.5-3 hours air dry.
Buff PC-47 Rapid Cure Clearcoat after 1.5-3 hours air dry.
Use of **PC-81 Urethane Accelerator** to increase dry times is not recommended.




Clean HVLP spray gun and cup in a device that recirculates solvents during cleaning that collects used solvent and minimizes evaporation. Do not leave catalyzed clear in spray gun longer than 2 hours.
Clean spray gun and cup immediately.

ACTIVATORS USED:

PC4XAF	FAST	60°F
PC4XAN	NORMAL	70°F
PC4XAS	SLOW	80°F
PC4XAES	EXTRA SLOW	90°F

MIX 3 PARTS CLEAR
1 PART ACTIVAT
1 PART REDUCER



Painters Choice Technologies PC-47 Rev. 2/10
866-228-6528

Appearance:	Clear liquid
Flash point:	<0°F TCC
Pot life:	4 hours at 75°F
Gloss:	92 Plus
Mix Ratio:	3:1:1
Coverage 1 mil.:	602 sq. ft.
Weight Solids:	37.6%
Sprayability Viscosity:	18 sec. #2 Zahn
V.O.C.:	RTS 4.2lbs./Gal mixed 3:1:1 with PC4X Activators.